

Table 2.7-9. Typical Proximate Analysis of In-situ Coal at the Trapper Mine

Parameters Analyzed ¹	Coal Seam						
	F	G	H	I	K-L-M	Q	R
% Moisture	18.39	17.88	12.02	12.19	18.10	14.18	14.84
% Ash	5.62	6.59	5.93	4.86	3.47	5.99	4.43
% Fixed Carbon	42.95	43.13	36.24	40.22	47.21	42.54	45.45
% Sulfur	0.66	0.73	0.68	0.43	0.26	0.35	0.42
BTU/lb	10,155	10,053	10,747	10,862	10,400	10,364	10,479

¹ Data Analyzed by Commercial Testing and Engineering Laboratory,
Denver, Colorado.